



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

REC'D 27 MAY 2004

WIPO

PCT

Bescheinigung

Certificate

Attestation

Die angehefteten Unterlagen stimmen mit der ursprünglich eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.

The attached documents are exact copies of the European patent application described on the following page, as originally filed.

Les documents fixés à cette attestation sont conformes à la version initialement déposée de la demande de brevet européen spécifiée à la page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

03007141.9

**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk

BEST AVAILABLE COPY



Anmeldung Nr:
Application no.: 03007141.9
Demande no:

Anmeldetag:
Date of filing: 28.03.03
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

BIOPHARM
GESELLSCHAFT ZUR BIOTECHNOLOGISCHEN
ENTWICKLUNG VON PHARMAKA mbH
Czernyring 22
69115 Heidelberg
ALLEMAGNE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se référer à la description.)

Improved Osteoinductive Materials

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

A61L27/00

Am Anmeldetag benannte Vertragsstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LU MC NL
PT SE SI SK TR LI

28. März 2003

WEICKMANN & WEICKMANN

Patentanwälte
European Patent Attorneys · European Trademark Attorneys

EPO - Munich
75

28. März 2003

Unser Zeichen:
29725P EP/BBsh

DIPL.-ING. H. WEICKMANN (bis 31.1.01)
DIPL.-ING. F. A. WEICKMANN
DIPL.-CHEM. B. HUBER
DR.-ING. H. LISKA
DIPL.-PHYS. DR. J. PRECHTEL
DIPL.-CHEM. DR. B. BÖHM
DIPL.-CHEM. DR. W. WEISS
DIPL.-PHYS. DR. J. TIESMEYER
DIPL.-PHYS. DR. M. HERZOG
DIPL.-PHYS. B. RUTTENSBERGER
DIPL.-PHYS. DR.-ING. V. JORDAN
DIPL.-CHEM. DR. M. DEY
DIPL.-FORSTW. DR. J. LACHNIT

Anmelder:
Biopharm Gesellschaft zur biotechnologischen Entwicklung von Pharmaka mbH
Czernyring 22

69115 Heidelberg

Improved Osteoinductive Materials

Improved Osteoinductive Materials

The present invention concerns osteoinductive materials comprising matrix materials and morphogenetic proteins, wherein depending on the subject matter the proteins may
5 be dimeric or monomeric proteins. The osteoinductive materials according to the present invention have improved properties. The invention concerns further methods for producing the respective improved osteoinductive materials.

Many growth factors of the TGF- β superfamily (Kingsley, Genes and Development 8,
10 133-146 (1994) as well as the references cited therein) are relevant for a wide range of medical treatment methods and applications which in particular concern promotion of cell proliferation and tissue formation, including wound healing and tissue reproduction. Such growth factors in particular comprise members of the TGF- β (transforming growth factor, cf. e.g. Roberts and Sporn, Handbook of Experimental
15 Pharmacology 95 (1990), page 419-472, editors: Sporn and Roberts), the DVR-group (Hötten et al., Biochem. Biophys. Res. Comm. 206 (1995), page 608-613 and further literature cited therein) including BMPs (bone morphogenetic protein, cf. e.g. Rosen and Thies, Growth Factors in Perinatal Development (1993), page 39-58, editors: Tsang, Lemons and Balistreri) and GDFs (growth differentiation factors), the
20 inhibin/activin (cf. e.g. Vale et al., The Physiology of Reproduction, second edition (1994), page 1861-1878, editors: Knobil and Neill) and the GDNF protein family (Rosenthal, Neuron 22 (1999), page 201-203; Airaksinen et al. Mol Cell Neurosci 13 (1999), page 313-325). Although the members of the TGF- β superfamily show high amino acid homologies in the mature part of the protein, in particular 7 conserved
25 cysteines, they show considerable variations in their exact functions. Often individual growth factors of these families exhibit a plurality of functions at the same time, so that their application is of interest in various medical indications. Some of these multifunctional proteins also have survival promoting effects on neurons in addition to functions such as e.g. regulation of the proliferation and differentiation in many cell types
30 (Roberts and Sporn, supra; Sakurai et al., J. Biol. Chem. 269 (1994), page 14118-14122). Thus e.g. trophic effects on embryonic motoric and sensory neurons were demonstrated for TGF- β *in vitro* (Martinou et al., Dev. Brain Res. 52, page 175-181 (1990) and Chalazonitis et al., Dev. Biol. 152, page 121-132 (1992)). In addition, effects promoting survival of dopaminergic neurons are shown for TGF- β -1,

-2, -3, activin A and GDNF, a protein which has structural similarities to TGF- β superfamily members. (Kriegstein et al., EMBO J. 14, page 736-742 (1995)).

The occurrence of proteins of the TGF- β superfamily in various tissue stages and development stages corresponds with differences with regard to their exact functions as well as target sites, life span, requirements for auxiliary factors, necessary cellular physiological environment and/or resistance to degradation.

The proteins of the TGF- β superfamily exist as homodimers or heterodimers having a single disulfide bond in nature. However, it was discovered that also proteins lacking the cysteine responsible for dimer formation maintain the characteristic properties of the dimeric wild-type proteins at least to a substantial extent. Such forms may have advantages over the dimeric proteins, especially when ease of production, i.e. reproducible, simple and inexpensive production by genetic engineering methods is concerned. Examples for such proteins and their production as well as their use are described in WO01/11041.

Mainly for applications in the bone related field, like e.g. repair of bone defects or bone regeneration, filling in of bone defects caused by disease, trauma or operation or degenerative bone defects etc., but also for cartilage, connective tissue such as tendon or ligament, dental, neurological, angiogenetic or other applications it is useful to combine morphogenetic proteins with matrix materials. Such matrix materials which are coated or soaked with morphogenetic proteins can provide a device for continuous release of morphogenetic protein and therefore constant stimulation of progenitor cells to differentiate and form new cells of the damaged kind of tissue. Additionally the matrix material may provide a favourable environment for adhesion and ingrowth of proliferating cells and thereby accelerate formation of new tissue, especially bony tissue.

Such uses of morphogenetic proteins in combination with matrix materials are extensively published and described, such as for example in WO98/21972. However there is still a need for materials which contain high amounts of morphogenetic proteins in a form which provides continuous release of protein. Homogeneous and maximal coating of matrix materials with morphogenetic proteins is a crucial factor for successful osteoinductive materials and is still an object to be solved. One main problem is the limited solubility of morphogenetic proteins. State of the art osteoinductive materials produced often contain only small amounts of active

morphogenetic proteins since they are unstable or bound nonuniformly to the matrix surfaces. Especially inner surfaces of porous matrix materials are coated insufficiently.

It was therefore an object of the present invention to provide improved osteoinductive materials for use in the pharmaceutical field and especially to provide methods to obtain matrix materials which are efficiently coated with morphogenetic proteins.

This issue is solved according to the present invention by providing osteoinductive materials as described herein and in the attached claims.

10

In order to avoid misunderstandings and ambiguities, some frequently used terms herein are defined and exemplified as follows:

The term "morphogenetic protein" as used herein means a protein of the TGF- β superfamily or a biologically active part or variant thereof. This term comprises all proteins which contain at least a 7 cysteine region characteristic for TGF- β superfamily proteins, regardless whether the cysteine responsible for dimer formation present in this domain has been replaced by another amino acid or not. Interesting members of the TGF- β superfamily or biologically active parts or variants thereof are e.g. the TGF- β proteins like TGF- β 1, TGF- β 2, TGF- β 3, TGF- β 4, TGF- β 5 (U.S. 5,284,763; EP 0376785; U.S. 4,886,747; DNA 7 (1988), page 1-8), EMBO J. 7 (1988), page 3737-3743), Mol. Endo. 2 (1988), page 1186-1195), J. Biol. Chem. 265 (1990), page 1089-1093), OP1, OP2 and OP3 proteins (U.S. 5,011,691, U.S. 5,652,337, WO 91/05802) as well as BMP2, BMP3, BMP4 (WO 88/00205, U.S. 5,013,649 and WO 89/10409, Science 242 (1988), page 1528-1534), BMP5, BMP6 and BMP-7 (OP1) (Proc. Natl. Acad. Sci. 87 (1990), page 9841-9847, WO 90/11366), BMP8 (OP2) (WO 91/18098), BMP9 (WO 93/00432), BMP10 (WO 94/26893), BMP11 (WO 94/26892), BMP12 (WO 95/16035), BMP13 (WO95/16035), BMP15 (WO 96/36710), BMP16 (WO 98/12322), BMP3b (Biochem. Biophys. Res. Comm. 219 (1996), page 656-662), GDF1 (WO 92/00382 and Proc. Natl. Acad. Sci. 88 (1991), page 4250-4254), GDF8 (WO 94/21681), GDF10 (WO95/10539), GDF11 (WO 96/01845), GDF5 (CDMP1, MP52) (WO 95/04819; WO96/01316; WO 94/15949, WO 96/14335 and WO 93/16099 and Nature 368 (1994), page 639-643), GDF6 (CDMP2, BMP13) (WO 95/01801, WO 96/14335 and WO95/16035), GDF7 (CDMP3, BMP12) (WO 95/01802 and WO 95/10635), GDF14 (WO 97/36926), GDF15 (WO 99/06445), GDF16 (WO 99/06556),

60A (Proc. Natl. Acad. Sci. 88 (1991), page 9214-9218), DPP (Nature 325 (1987), page 81-84), Vgr-1 (Proc. Natl. Acad. Sci. 86 (1989), page 4554-4558) Vg-1, (Cell 51 (1987), page 861-867), dorsalin (Cell 73 (1993), page 687-702), MIS (Cell 45 (1986), page 685-698), pCL13 (WO 97/00958), BIP (WO 94/01557), inhibin a, activin BA and
 5 activin BB (EP 0222491), activin BC (MP121) (WO 96/01316), activin BE and GDF12 (WO 96/02559 and WO 98/22492), activin BD (Biochem. Biophys. Res. Comm. 210 (1995), page 581-588), GDNF (Science 260 (1993), page 1130-1132, WO 93/06116), Neurturin (Nature 384 (1996), page 467-470), Persephin (Neuron 20 (1998), page 245-253, WO 97/33911), Artemin (Neuron 21 (1998), page 1291-1302), Mic-1 (Proc.
 10 Natl. Acad. Sci USA 94 (1997), page 11514-11519), Univin (Dev. Biol. 166 (1994), page 149-158), ADMP (Development 121 (1995), page 4293-4301), Nodal (Nature 361 (1993), page 543-547), Screw (Genes Dev. 8 (1994), page 2588-2601). Furthermore, also non naturally occurring and therefore artificially produced proteins of the TGF- β superfamily are included in the term "morphogenetic proteins", such as e.g. proteins of
 15 the TGF- β superfamily lacking a cysteine responsible for dimer formation as e.g. described in WO 01/11041. Other useful proteins also included in the definition "morphogenetic protein" are biologically active biosynthetic constructs including biosynthetic proteins designed using sequences from two or more known morphogenetic proteins. Examples of biosynthetic constructs are disclosed in U.S.
 20 5,011,691 (e.g. COP-1, COP-3, COP-4, COP-5, COP-7 and COP-16). The disclosure of the cited publications including patents or patent applications are incorporated herein by reference. Most of the members of the TGF- β protein superfamily are morphogenetic proteins that are useful for treatments where regulation of differentiation and proliferation of cells or progenitor cells is of interest. This can result in replacement of
 25 damaged and/or diseased tissue like for example skeletal (bone, cartilage) tissue, connective tissue, periodontal or dental tissue, neural tissue, tissue of the sensory system, liver, pancreas, cardiac, blood vessel, skin and renal tissue, uterine or thyroid tissue etc. Morphogenetic proteins are often useful for the treatment of ulcerative or inflammatory tissue damage and wound healing of any kind such as enhanced healing
 30 of ulcers, burns, injuries or skin grafts.

The term "biologically active part or variant thereof" as used herein means protein fragments retaining activity, precursor proteins that are e.g. cleaved at the site of activity to the mature form or show biological activity themselves, or also protein

variants that still maintain essentially the biological activity of the wild-type protein. Such variants preferably contain conservative amino acid substitutions, but especially at the N-terminal part of the mature proteins even considerable deletions or substitutions do not lead to a considerable loss of biological activity. Persons skilled in the art are well able to determine whether a certain protein shows the required biological activity. Proteins showing at least 70% and preferably at least 80% homology to the mature wild-type proteins should be understood as encompassed by the present invention. According to this definition, proteins lacking a cysteine residue responsible for dimer formation in respective naturally occurring proteins are not considered variants of the respective dimeric wildtype proteins, since the molecular weights of these proteins are only half of that of their respective dimeric counterparts and therefore the above mentioned homology criteria are not fulfilled.

The term "homology" as used herein means that amino acids within the following groups are considered homologous: "S, T, P, A, G" and "N, Q, D, E" and "H, R, K" and "M, I, L, V" and "F, Y, W", not counting gaps due to the sequence alignment.

The term "matrix material" as used herein means a carrier matrix acting as a scaffold for cell recruitment, attachment, proliferation and differentiation and/or as a potential delivery and storage device for morphogenetic proteins. All types of matrix materials are useful in accordance with the present invention, as long as they are biocompatible and selected for the intended area or indication of use. The matrix material can be a natural material, a modified natural material as well as a synthetic material. All already known matrices for morphogenetic proteins are encompassed. Examples of natural materials are e.g. autologous, heterologous or xenologous bone materials, collagen, e.g. collagen type I and III, or metals like titanium. Also other components of the extracellular matrix can be used. The extracellular matrix comprises for example the various collagens, as for example types I, II, V, IX, X, XI and XIII, further hydroxyl apatite, proteoglycans and glycosaminoglycans, as for example chondroitinsulfate, biglycan, decorin and/or hyaluronic acid, or noncollagenous proteins as for example osteopontin, laminin, fibronectin, vitronectin, thrombospondin, cartilage matrix protein and dentin phosphoprotein. All mentioned natural materials may also be used in artificially modified forms.

Examples of modified natural materials are demineralized bone, thermoashed bone mineral, sintered bone or chemically crosslinked hyaluronic acid (hydrogel), or metal alloys.

5 Examples of synthetic materials are polymers like polyglycolic acid, polylactide and polylactide derivatives such as e.g. polylactic acid, poly(lactide-co-glycolide), polylactid acid-polyethylene glycol or glycolide L-lactide copolymers, further polyphosphates, polyethylene glycol, polyoxyethylene polyoxypropylene copolymers or materials containing calcium phosphates such as beta-tricalcium phosphate ($\text{Ca}_3(\text{PO}_4)_2$), alpha-tricalcium phosphate and hydroxyl apatite.

10 Further examples of other useful carrier matrices belonging to one of the above mentioned groups are $\text{Ca}(\text{OH})_2$, coral, natural bone mineral, chitin, non-demineralized bone particles, ceramic bone particles, ceramic dentin, irradiated cancellous bone chips, plaster of Paris, bioactive glass, apatite-wollastonite-containing glass ceramic. Also a combination of the above mentioned carrier matrices can form the matrix material as
15 for example the combination of hydroxy apatite and collagen (e.g. Healos, previously available from Orquest, Inc., CA, USA, [now DePuy Acromed, MA, USA]), a combination of polyglycolic acid and polylactic acid or polylactid derivatives, or coral-collagen composites. For a non limiting list of useful carrier matrices see further Kirker-Head, Advanced Drug Delivery 43 (2000), page 65-92.

20

The term "osteoinductive material" as used herein means a biological device comprising at least a matrix material and a morphogenetic protein temporarily immobilized within and/or on the surface of said matrix material. Furthermore, the device may comprise additives that are useful for the envisaged application. Such
25 substances include for example, but are not limited to antibiotics, antifibrinolytic agents, vitamins, stabilizers, buffers, emulgators, antiinflammatory substances or other additives which enhance the solubility of the morphogenetic protein. It is a prerequisite for such substances that they are not harmful to the patient and do not disturb the intended pharmaceutical application. The term "osteoinductive material" according to
30 the present invention is not meant to be limited to the use in the area of bone repair. Also for other indications, such as for example for the repair or growth of cartilage, connective tissue including tendon and/or ligament, periodontal or dental tissue, neural tissue, tissue of the sensory system, liver, pancreas, cardiac, blood vessel, renal, uterine, and thyroid tissue, skin, mucous membranes, endothelium, epithelium, for promotion or

induction of nerve growth, tissue repair and regeneration, angiogenesis, wound healing including ulcers, burns, injuries or skin grafts, induction of proliferation of progenitor cells or bone marrow cells, the use of a combination of protein and matrix material can be useful to e.g. take advantage of slow continuous release of protein and/or providing an environment that enables cells to grow in and thus support formation of new healthy tissue. Rather the term "osteoinductive material" is used because of the meaning it has already acquired in the state of the art as combination of matrix materials and morphogenetic proteins. The osteoinductive materials according to the invention are useful in all instances where morphogenetic proteins are beneficially applied, and especially where morphogenetic proteins are applied together with a matrix material to provide for slow and sustained release of protein and/or to provide an environment that further facilitates and enhances cell proliferation and tissue regeneration. The osteoinductive materials according to the present invention contain a maximal dosage of morphogenetic proteins in a biologically active and effective form in and/or on the surfaces of the preferably porous matrix material.

The terms "evenly coated" and "evenness of coating" as used herein mean that each mm^2 of the surface of the osteoinductive material contains basically equal amounts of morphogenetic proteins.

Osteoinductive materials described in the art often exhibit an uneven distribution of the bioactive morphogenetic proteins on the carrier. In most of these cases either less protein is being bound on some parts of the matrix or a considerable percentage of the bound protein displays reduced bioactivity. According to the present invention it has been found that this unevenness is mainly influenced by local precipitation events which take place during the coating of the matrix materials together with protein degradation processes. Thus, the osteoinductive capability of the device is significantly reduced. Such uneven distribution and protein degradation can be avoided by modifying or enhancing both protein stability and solubility during the coating process, which is attainable by skilful selection and control of the pH conditions as well as by the use of the suitable buffer or solvent characteristics and specific additives.

The solubility of morphogenetic proteins in liquids depends, besides other important factors also disclosed herein, upon the pH value of the solvent. Coating of a matrix material with morphogenetic proteins is most efficient, if the proteins are completely dissolved within the coating solution in a stable manner during the whole term of the coating procedure. However, since most matrix materials are either donators or acceptors of hydrogen ions, the matrix materials themselves affect the pH during the coating process. The surface of most matrix materials is maximized and contains countless cavities and pores, which exhibit local microenvironments with sometimes different pH conditions, where the proteins tend to precipitate. The methods of the present invention allow the protein solution to distribute evenly across the inner surface of the carrier material and to bind homogenously and stable to these surfaces without the danger of a pH-induced precipitation of said protein.

This evenness of coating and especially the effective adsorption of morphogenetic proteins to the matrix material according to the present invention is therefore achieved by providing the proteins stable and completely dissolved in a solution. In general, the solvent for the morphogenetic proteins used within the coating procedure has to stabilize the proteins and to compensate critical pH shifts caused by the carrier. According to this invention, exact knowledge of the pH-dependent solubility of the morphogenetic proteins together with a basic knowledge of the matrix characteristics allows to choose a suitable solvent or buffer for the coating procedure. For example, if the morphogenetic proteins are soluble at a pH less than 4.5 but precipitate at higher pH values, and the matrix material itself has alkaline properties, the solvent or buffer used within the coating procedure should contain suitable substances, preferably a weak acid, to compensate for the pH shift caused by the carrier in order to keep the morphogenetic proteins efficiently in solution during the whole coating process. If the morphogenetic proteins are soluble at a pH above 10 but precipitate at lower pH values, and the matrix material itself has acidic properties, the solvent or buffer used within the coating procedure should contain other suitable substances, preferably a weak base, for efficient compensation. Examples describing the influence of different matrices on the pH as well as the pH-dependent solubilities of several morphogenetic proteins are given herein. According to the other embodiments of the present invention which are not explicitly exemplified, a person skilled in the art is well able to easily determine the

influence of any other matrix on the pH as well as the specific pH-dependent solubility for any other morphogenetic protein.

The morphogenetic proteins of this invention precipitate at physiological (nearly neutral) or slightly acidic/basic pH values, whereas they are soluble at pH values below 4.5 and above 10.3, if the solvents exhibit ionic concentrations of 100 mmol/l or more. Surprisingly this pH-dependent solubility of the morphogenetic proteins can be additionally modified by changing the composition or concentration of the buffers or solvents, therefore leading to a clearly enlarged pH range in which a even and stable coating of matrix materials is possible. In solvents with lower ionic concentrations such as e.g. 10 or 20 mmol/l, protein solubilities of at least 75 µg/ml, preferably 100 µg/ml, more preferably 150 µg/ml and most preferably more than 200 µg/ml are achievable at pH values below 5.2 and above 9.5. This enlarged pH range is especially favourable if pH-sensitive matrices, e.g. matrices comprising natural materials, are coated.

15

According to this aspect of the invention, the pH-dependent solubility of the morphogenetic protein and the stable coating of the matrix material is dependent upon the ionic concentration of the used buffer or solvent and can be strongly improved by using a buffer or solvent of low ionic concentration. Preferably, said buffer or solvent has a concentration of 150 mmol/l or less, preferably 100 mmol/l or less, 80 mmol/l or less, 40 mmol/l or less, 20 mmol/l or less, 10 mmol/l or less, or 5 mmol/l. More preferably, the buffer or solvent has a concentration of 20 mmol/l. Most preferably, the buffer or solvent has a concentration of 10 mmol/l.

25

It has furthermore been found that also the solvent composition influences the pH-dependent solubility of the morphogenetic protein and the stable coating of the matrix material. Whereas buffers containing either sodium citrate, 2-amino-2-methyl-1,3-propanediol-HCl or sodium glycine have been proven to be unsuited as solvents for the morphogenetic proteins, remarkable good protein stability or solubility has been obtained in solvents containing sodium acetate, sodium carbonate or in unbuffered solutions containing HCl or NaOH. Additionally, good protein solubility has unexpectedly been found in solutions comprising organic solvents such as trifluoroacetic

30

acid (TFA), TFA/ethanol compositions, isopropanol, propanol, butanol, isopropanol, dimethyl sulfoxide or acetone.

5 According to this aspect of the present invention, the buffer or solvent for the morphogenetic proteins contains preferably an acid such as e.g. acetic acid or hydrochloric acid or a base such as e.g. NaOH. More preferably, the solvent is a buffer containing sodium acetate or sodium carbonate. Also preferably, the solvent contains more than 25%, 30%, 40%, 50%, 75% or 100% organic solvents.

10 It was additionally quite unexpected that the morphogenetic proteins are not solely soluble but also maintain their biological activity at strongly acidic (below pH 5.2) as well as at strongly basic pH values (above pH 9.5) which rarely occur under physiological conditions. These results allow the development of specific matrix materials and coating methods thereof. Solutions of active morphogenetic proteins
15 having these extreme pH values are supporting sterility. Because of this they can be used advantageously within the coating procedure since the danger of an undesired contamination with viable microorganisms is significantly reduced. On top of that, coating at e.g. basic pH between 9.5 and 12 is in some cases beneficial because several matrices degrade in acidic milieus and therefore need basic pH conditions during the
20 coating. Furthermore, coating of matrix materials which have neutral or basic properties by themselves can be performed at high pH values and generally excludes the risk of precipitation of the protein during the coating procedure. For example, $\text{Ca}(\text{OH})_2$ is a material routinely used in tooth repair procedures but exhibits a pH value of about 12 in aqueous solutions, which normally prevents a coating with proteins. $\text{Ca}(\text{OH})_2$ has been
25 previously shown to stimulate the formation of minor amounts of secondary dentin. This effect can be dramatically enhanced by coating of the $\text{Ca}(\text{OH})_2$ at pH12 with the morphogenetic proteins according to this invention.

30 The data summarized above enable, in a specific embodiment of the present invention, a coating of matrix materials with biologically active morphogenetic proteins at pH values below pH 5.2 and at particularly high pH between 9.5 and 13. Preferred are pH values between 12 and 13. Especially preferred are pH values between 2 and 4.5, between 4.5 and 5.2, between 9.5 and 10.3 and between 10.3 and 12. and between 12 and 13.

The coating of a matrix material can be furthermore strongly improved by using stabilizers, emulgators and other auxiliaries and additives which e.g. prevent their degradation or enhance their solubility. Especially preferred are polyethylene glycols which dramatically enhance the solubility of the morphogenetic proteins if covalently or noncovalently bound to the proteins. Other useful additives and auxiliaries can be substances that are e.g. beneficial for the uniform adsorption of protein on matrix material as well as substances that stabilize the protein in solution. Furthermore any substance may be included, as long as it has a positive effect in any way or is at least not harmful for the patient. Examples for useful substances are nonionic detergents like Tween80, basic amino acids, carrier proteins like serum albumin, alkaline salts of fatty acids (soaps) or syndets (synthetic detergents other than soaps), sugars or alcohols like e.g. sucrose, mannit/mannitol (WO98/33514), ethanol or isopropanol. Especially sugars and alcohols as well as soaps and syndets have been found to improve the evenness of the coating. These solutions containing alcohols, soaps and syndets are very advantageous because of their very low surface tension, which improves the effectivity of coating. In injectable matrix materials and formulations useful for parenteral administration, soaps and syndets are helpful because they form micellar structures. Those micelles are capable of surrounding and emulsifying the hydrophobic morphogenetic proteins, thereby supporting protein delivery and preventing precipitation. Since soaps have basic properties with pH values above 8, they can be easily combined with the morphogenetic proteins of the present invention, which have been proven to remain biologically active at those basic pH values. In the acidic pH range below 5.2, syndets instead of soaps can be used in combination with the morphogenetic proteins.

Also other substances like antibiotics, antiseptics, vitamins, anti-fibrinolytics etc. can be added if desired.

In detail, the coating of a matrix material according to the present invention can be strongly improved according to the present invention by using one or more saccharides as additives. Preferably, said saccharide is sucrose. Also preferably, said saccharide is mannit. Especially preferred are coating solutions which include 8%, 10%, 12%, 15% or 20% saccharides.

Additionally, the coating of a matrix material can be strongly improved by using one or more alcohols as additives. Preferably, said alcohol is ethanol. Also preferably, said alcohol is isopropanol. Especially preferred are coating solutions which include 50%, 55%, 60% or 65% alcohols.

5

Furthermore, the coating of a matrix material as well as the composition of injectable carriers or parenteral formulations of the morphogenetic proteins can be improved by using alkaline salts of fatty acids (soaps) as additives. Preferably, said soap is sodium stearate, sodium myristate, sodium oleate or sodium palmeate. Especially preferred are solutions which include 10%, 20%, 30%, 40%, 50% or 75% soaps.

10

The coating of a matrix material as well as the composition of an injectable or parenteral formulation of the morphogenetic proteins can be also improved by using alkaline salts of syndets as additives. Preferably, said syndet is an linear alkyl sulfonate, an alkyl sulfuate, or an alkyle benzene sulfonate. More preferably, said syndet is an laurel or laureth sulfate. Most preferably, said syndet is sodium or ammonium lauryl sulfate. Especially preferred are solutions which include 10%, 20%, 30%, 40%, 50% or 75% syndets.

15

One aspect of the present invention provides an osteoinductive material comprising a matrix material and adsorbed on outer or inner surfaces of this matrix material one or more morphogenetic protein(s), wherein the osteoinductive material is obtainable by contacting the matrix material and the morphogenetic protein under suitable conditions to keep the protein dissolved in a solution thereby allowing that the matrix material is evenly coated with the morphogenetic protein. This matrix material is acting as a scaffold for cell recruitment, attachment, proliferation and/or differentiation and as a potential delivery and storage device for morphogenetic proteins. In a preferred embodiment, the matrix material is a porous material and allows penetration of a solution of the protein to the inner surfaces of the material. Also preferably, the matrix material is a natural material, a modified natural material or a synthetic material. Even more preferably, the matrix material contains a type of calcium phosphate, especially beta-tricalcium phosphate ($\text{Ca}_3(\text{PO}_4)_2$), alpha-tricalcium phosphate and hydroxyl apatite. Also especially preferred are the following matrix materials: a) collagen, b)

25

30

Ca(OH)₂, c) polylactide derivatives: polylactide, polylactic acid, poly(lactide-co-glycolide), polylactid acid-polyethylene glycol, d) hyaluronic acid e) polyoxyethylene polyoxypolypropylene copolymers. Also especially preferred is a combination of hydroxy apatite and collagen (e.g. Healos, previously available from Orquest, Inc., CA, USA, [now DePuy Acromed, MA, USA]).

The morphogenetic proteins comprised in the osteoinductive material are proteins belonging to the TGF- β superfamily or biologically active parts or variants thereof, which can be dimeric or lack the cysteine responsible for dimer formation.

10

All TGF- β superfamily members contain a specific domain called "7 cysteine region". This specific 7 cysteine region is considered to be the most important part of the proteins in view of the biological activity. Therefore proteins retaining this critical region are preferred proteins according to the invention. In this region the respective location of the cysteine residues to each other is important and is only allowed to vary slightly in order not to lose the biological activity. Consensus sequences for such proteins are known in the state of the art and all proteins complying with such consensus sequences are considered to be encompassed by the present invention. It is especially preferred that proteins according to this aspect of the invention contain at least the 7 cysteine region characteristic for the TGF- β protein superfamily, regardless whether the cysteine responsible for dimer formation present in this domain has been replaced by another amino acid or not.

In a preferred embodiment the morphogenetic protein or biologically active part or variant thereof is a mature protein or a biologically active part or variant thereof.

Also preferably, the morphogenetic protein or biologically active part or variant thereof is a member of the TGF- β superfamily subgroups called TGF- β , BMP-, GDF-, activin- or GDNF-families.

Several BMP proteins which were originally discovered by their ability to induce bone formation have been described. Meanwhile, several additional functions have been found as it is also true for members of the GDFs. These proteins show a very broad field of applications and especially are in addition to their bone and cartilage growth promoting activity (see for example: WO 88/00205, WO 90/11366, WO 91/05802)

useful in periodontal disease, for inhibiting periodontal and tooth tissue loss, for sealing tooth cavities, for enhancing integration of a tooth in a tooth socket (see for example: WO 96/26737, WO 94/06399, WO 95/24210), for connective tissue such as tendon or ligament (see for example: WO 95/16035), for improving survival of neural cells, for inducing growth of neural cells and repairing neural defects, for damaged CNS tissue due to stroke, trauma or degenerative diseases (see for example: WO 97/34626, WO 94/03200, WO 95/05846), for maintaining or restoring sensory perception (see for example WO 98/20890, WO 98/20889), for renal failure (see for example: WO 97/41880, WO 97/41881), for liver regeneration (see for example WO 94/06449), for regeneration of myocardium (see for example WO 98/27995), for treatment or preservation of tissues or cells for organ or tissue transplantation, for integrity of gastrointestinal lining (see for example WO 94/06420), for increasing progenitor cell population as for example hematopoietic progenitor cells by *ex vivo* stimulation (see for example WO 92/15323) etc..

More preferably, the morphogenetic protein or biologically active part or variant thereof is a dimeric protein belonging to the TGF- β , BMP-, GDF-, activin- or GDNF-families. Even more preferably, the dimeric morphogenetic protein or biologically active part or variant thereof is BMP2, BMP7, BMP12 or BMP13.

Most preferably, the dimeric protein contained in the osteoinductive material according to the invention is protein MP52 (also termed GDF5 or CDMP-1) or a biologically active part or variant thereof. The MP52 sequence is shown in SEQ.ID.NO.1 (DNA and protein sequence) and SEQ.ID.No.2 (protein sequence, only), whereas the Xaa at position 465 represents cysteine. SEQ.ID.NO.2 shows the complete protein sequence of the prepro protein of human MP52 as already disclosed in WO 95/04819. The start of the mature protein lies preferably in the area of amino acids 352-400, especially preferred at amino acids 381 or 382. Therefore, the mature protein comprises amino acids 381-501 or 382-501. The first alanine of the mature protein can be deleted and the mature protein then preferably comprises amino acids 383-501.

Applications for MP52 reflect several of the already described applications for the BMP/GDF family. MP52 is considered to be a very effective promoter of bone and cartilage formation as well as connective tissue formation (see for example WO 95/04819, Hötten et al., (1996), Growth Factors 13, 65-74, Storm et al., (1994) Nature

368, 639-643, Chang et al., (1994) J. Biol. Chem. 269 (45), 28227-28234). In this connection MP52 is useful for applications concerning the joints between skeletal elements (see for example Storm & Kingsley (1996) Development 122, 3969-3979). One example for connective tissue is tendon and ligament (Wolfman et al., (1997), J. Clin. Invest. 100, 321-330, Aspenberg & Forslund (1999), Acta Orthop Scand 70, 51-54, WO 95/16035). MP52 is also useful for tooth (dental and periodontal) applications (see for example WO 95/04819, WO 93/16099, Morotome et al. (1998), Biochem Biophys Res Comm 244, 85-90). MP52 is useful in wound repair of any kind. It is in addition very useful for promoting tissue growth in the neuronal system and survival of dopaminergic neurons, for example. MP52 in this connection is useful for applications in neurodegenerative diseases like e.g. Parkinson's disease and possibly also Alzheimer's disease for Huntington chorea tissues (see for example WO 97/03188, Kriegstein et al., (1995) J. Neurosci Res. 42, 724-732, Sullivan et al., (1997) Neurosci Lett 233, 73-76, Sullivan et al. (1998), Eur. J. Neurosci 10, 3681-3688). MP52 allows to maintain nervous function or to retain nervous function in already damaged tissues. MP52 is therefore considered to be a generally applicable neurotrophic factor. It is also useful for diseases of the eye, in particular retina cornea and optic nerve (see for example WO 97/03188, You et al. (1999), Invest Ophthalmol Vis Sci 40, 296-311), and for hair growth and the treatment and diagnosis of skin related disorders (WO 02/076494).

Like in the already above mentioned definition of these terms, MP52 can e.g. be used in its mature form, however, it can also be used as a fragment thereof containing at least the 7 cysteine region or also in a precursory form. Deviations at the N-terminal part of mature MP52 do not affect its activity to a considerable degree. Therefore, substitutions or deletions within the first 9 amino acids or additions on the N-terminal part of the proteins are still within the scope of the present invention. It might be useful to add a peptide to the N-terminal part of the protein, e.g. for purification reasons. It might not be necessary to cleave off this added peptide after expression and purification of the protein. Additional peptides at the N- or C-terminal part of the protein may also serve for the targeting of the protein to special tissues such as nerve or bone tissue or for the penetration of the blood/brain barrier.

Also more preferably, the morphogenetic protein or biologically active part or variant thereof is a protein belonging to the TGF- β , BMP-, GDF-, activin- or GDNF-families

but lacking a cysteine residue which is responsible for dimer formation in respective naturally occurring proteins. The protein according to this aspect of the present invention cannot form the disulfide bridge which is present in the wildtype form of the protein. As described in WO01/11041, substitution or deletion of the cysteine, which

5 normally effects the dimerization in the proteins, results upon expression and correct folding (proper formation of the intramolecular disulfide bridges) in a monomeric protein that retains the biological activity of the dimeric form. Generally, also fusion proteins of a monomeric protein according to this aspect of the invention and another peptide or group are considered within the scope of the present invention, wherein these

10 other peptides or groups are directing the localization of the fusion protein, e.g. because of an affinity to a certain tissue type etc. Examples for such fusion proteins are described in WO 97/23612. The protein containing such addition will retain its biological activity at least as long as such addition does not impair the formation of the biologically active conformation of the protein.

15 Although the biological activities of monomeric and (wildtype) dimeric proteins are comparable, dimeric proteins exhibit some deviating chemical and biophysical properties. Because of their doubled molecular weight as well as the persisting covalent linkage and intermolecular forces between the two monomeric subunits, dimers expose more and also other amino acid residues to the surrounding medium than their

20 monomeric equivalents. Dimers consist of two covalently connected subunits which are under all physiological circumstances in close distance to each other, thereforee creating multiple types of reciprocal interactions with themselves as well as with the solvent. It is disclosed in the state of the art which amino acid is responsible in a certain protein family or protein for dimer formation (see for example: Schlunegger & Grutter

25 (1992) Nature 358, 430-434; Daopin et al., (1992) Science 257, 369-373 and Griffith et al., Proc. Natl. Acad. Sci. 93 (1996), page 878-883). Especially the amino acids in close distance to this linkage point between the subunits are never in direct contact with the solvent. Monomers, on the other hand, are usually surrounded entirely by the fluid and don't interact permantly with other monomeric molecules. These differences between

30 monomeric and dimeric morphogenetic proteins are theoretically expected to result in an altered pH-dependent solubility of the monomeric molecules. One further indication towards an altered solubility is given by the experimental determination of the isoelectric point (pI) of both proteins. The isoelectric point is defined as pH at which the

net charge of proteins at their pI is zero and the solubility of proteins at the pI reaches a minimum. As it is shown in example 1 and figure 1, the pI of the monomeric proteins according to this invention has been determined and it differs clearly from the pI of the dimeric proteins.

5

In view of this both theoretically and experimentally based prediction of altered solubilities of the monomeric morphogenetic proteins it has been absolutely unexpected that the pH-dependent solubility of the monomeric morphogenetic proteins is nevertheless equivalent to that of their dimeric equivalents.

10

The present invention is based on the further surprising results that also these monomeric proteins maintain their biological activity at extreme pH values and can be adsorbed on matrix materials without adverse effect on activity and efficiency. It was discovered during the work leading to the present invention that by providing certain pH conditions it is possible to keep monomeric proteins in solution even in presence of matrix materials. Under such conditions the soluble protein can uniformly adsorb to all surfaces attainable to the dissolved protein. The availability of inner surfaces of more or less porous materials will depend on the pore size. Using the conditions described in the present invention it will be possible to adsorb protein on all surfaces which are available to the solubilized protein due to its molecule size. The present invention avoids formation of precipitates and blockage of pores to further access of protein solution. This procedure achieves optimal coating of all available surfaces of the matrix material and the osteoinductive materials of the present invention show improved efficacy as compared to materials of the prior art.

20

25

As described in the above mentioned patent application WO01/11041, it was found that at least some of these monomeric proteins show a comparable or even higher activity, based on the weight of protein than their respective dimeric forms. A further important advantage lies in the fact that the proteins can be expressed in a large amount in prokaryotic hosts and upon simple refolding of the monomers they are obtained in high purity and very high yield without the need to separate dimerized from non dimerized (monomeric proteins). It is preferred that proteins according to this aspect of the invention contain at least the 7 cysteine region characteristic for the TGF- β protein superfamily. It is disclosed in the state of the art which cysteine is responsible in a

30

certain protein family or protein for dimer formation (see for example: Schlunegger & Grutter (1992) Nature 358, 430-434; Daopin et al., (1992) Science 257, 369-373 and Griffith et al., Proc. Natl. Acad. Sci. 93 (1996), page 878-883). This cysteine has to be deleted or substituted by another amino acid to form a protein used within the framework of this aspect of the present invention.

In an especially preferred embodiment of this aspect of the present invention the protein lacking a cysteine residue which is responsible for dimer formation contains a consensus sequence according to the following sequence

C C(Y)₂₅₋₂₉ C Y Y Y C (Y)₂₅₋₃₅ X C (Y)₂₇₋₃₄ C Y C (Formula I),

wherein C denotes cysteine, Y denotes any amino acid including cysteine and X denotes any amino acid except cysteine.

More preferably the protein lacking a cysteine residue which is responsible for dimer formation according to this aspect of the invention contains a consensus sequence according to the following sequence

C (Y)₂₈ C Y Y Y C (Y)₃₀₋₃₂ X C (Y)₃₁ C Y C (Formula II),

wherein C, X and Y have the same meaning as defined above.

Even more preferably the protein lacking a cysteine residue which is responsible for dimer formation according to this aspect of the invention contains a consensus sequence according to the following sequence

C (X)₂₈ C X X X C (X)₃₁₋₃₃ C (X)₃₁ C X C (Formula III),

wherein C and X have the same meaning as defined above.

In these consensus sequences especially preferred distances between the respective cysteine residues are contained, wherein also already the dimer forming cysteine is substituted by another amino acid. As with all proteins of said protein superfamily the location of and distance between the cysteines is more important than the identity of the other amino acids contained in this region. Therefore, the consensus sequence shows the respective location of the cysteines, but does not show the identity of the other amino acids, since these other amino acids are widely variable in the proteins of the TGF- β protein superfamily.

In an especially preferred embodiment the protein contained in the osteoinductive material is a monomeric form of MP52 and comprises the at least the mature part of the amino acid sequence according to SEQ.ID.NO.1 (DNA and protein sequence) and SEQ.ID.NO.2 (protein sequence, only), wherein the amino acid indicated by Xaa at

pos. 465 is either deleted or any amino acid except cysteine. Especially other hydrophobic amino acids such as glycine, valine, leucine or isoleucine can be present at pos. 465. The start of the mature protein lies preferably in the area of amino acids 352-400, especially preferred at amino acids 381 or 382. Therefore, the mature protein
5 comprises amino acids 381-501 or 382-501. The first alanine of the mature protein can be deleted and the mature protein then preferably comprises amino acids 383-501.

The most preferred protein used within the present invention is MP52-Ala83, a protein starting at amino acid 383 of SEQ.ID.NO.1 or 2, wherein the naturally occurring cysteine at position 465 is replaced by the hydrophobic amino acid alanine. Also for
10 MP52-Ala83, the mature protein starts preferably between amino acids 352-400, especially preferred at amino acids 381 or 382. The first alanine of the mature protein can be deleted and the mature protein then preferably comprises amino acids 383-501.

It is theoretically possible that proteins which correspond to the definition of
15 monomeric proteins as used in this context, form some kind of aggregates in solution. However, these aggregates do not correspond to dimers or multimers of proteins formed by defined intermolecular bridges and covalent binding. Nevertheless, van der Waals forces and other forms of weak binding can occur and such aggregates are considered to be encompassed by the present invention.

20

Another aspect of the present invention is a process for the production of an osteoinductive material of the invention. Said process comprises contacting a matrix material with a solution of morphogenetic protein(s) under suitable conditions to keep the protein stable and dissolved in a buffered solution and thereby allowing that the
25 matrix material becomes evenly coated with the morphogenetic proteins and subsequently drying of the coated matrix material. The process provides for selecting and adjusting the pH of the protein solution to a value of 5.2 or lower or 9.5 and higher, also when in contact with the matrix material. Preferred are pH values between 12 and 13. Especially preferred are pH values between 2 and 4.5, between 4.5 and 5.2, between
30 9.5 and 10.3 and between 10.3 and 12. Proteins and matrix materials that can form the osteoinductive materials are as described above for the other subjects of the present invention, also all suitable solvents/buffers, additives and auxiliaries.

The following nonlimiting examples together with the figures and sequence protocols are intended to further illustrate the invention.

SEQ.ID.NO.1 shows the DNA and protein sequence and SEQ.ID.NO.2 the protein sequence of MP52 and MP52-Ala83 prepro-peptides, wherein the amino acid indicated by Xaa at pos. 465 is either cysteine (in case of MP52) or alanine (in case of MP52-Ala83). The naturally occurring mature proteins MP52 and MP52-Ala83 comprise amino acids 382-501. In preferred recombinant variants of MP52 and MP52-Ala83, the first alanine of the mature protein is deleted and the mature protein comprises amino acids 383-501. In all following figures and examples, this recombinant versions of MP52 and MP52-Ala83 have been used.

Figure 1 shows the results of the isoelectric focusing according to example 1. MP52-Ala83 is present in lane 1, whereas MP52 is present in lane 2. The pI of MP52 is approximately 7.65 and the pI of MP52-Ala83 is approximately 7.1.

Figure 2 shows a comparison of the pH-dependent solubility of MP52 and MP52-Ala83 according to examples 2 and 3 and to the table below. The buffers (0.1 M sodium acetate-acetic acid (p. 429) and 0.1 M sodium carbonate-sodium bicarbonate (p. 439) were prepared according to Dawson et al.: Data for biochemical research (Third edition) 1986, p. 429 and p. 439, Clarendon Press, Oxford. Thus, concerning the pH-dependent solubility it can be stated that MP52 and MP52-Ala83 exhibit nearly identical properties.

SAMPLE	pH	SOLVENT	RECOVERY (%)	RECOVERY (µg/ml)
MP52-Ala83	9,50	Sodium carbonate 0.1 M	12,2	48,96
MP52-Ala83	9,87	Sodium carbonate 0.1 M	30,4	121,76
MP52-Ala83	10,08	Sodium carbonate 0.1 M	41,5	166,16
MP52-Ala83	10,29	Sodium carbonate 0.1 M	51,2	204,64
MP52-Ala83	10,49	Sodium carbonate 0.1 M	75,8	303
MP52-Ala83	10,79	Sodium carbonate 0.1 M	77,5	309,84
MP52-Ala83	11,07	Sodium carbonate 0.1 M	85,7	342,96
MP52-Ala83	11,28	Sodium carbonate 0.1 M	90,7	362,6
MP52-Ala83	11,49	Sodium carbonate 0.1 M	97,6	390,48
MP52-Ala83	11,70	Sodium carbonate 0.1 M	99,8	399,04
MP52-Ala83	11,87	Sodium carbonate 0.1 M	101,7	406,96
MP52-Ala83	12,10	Sodium carbonate 0.1 M	95,8	383,36
MP52	9,50	Sodium carbonate 0.1 M	2,1	8,32
MP52	9,87	Sodium carbonate 0.1 M	27,5	110,16

MP52	10,08	Sodium carbonate 0.1 M	34,7	138,8
MP52	10,29	Sodium carbonate 0.1 M	52,8	211,2
MP52	10,49	Sodium carbonate 0.1 M	54,8	219,12
MP52	10,79	Sodium carbonate 0.1 M	74,6	298,32
MP52	11,07	Sodium carbonate 0.1 M	77,6	310,32
MP52	11,28	Sodium carbonate 0.1 M	82,9	331,4
MP52	11,49	Sodium carbonate 0.1 M	94,6	378,56
MP52	11,70	Sodium carbonate 0.1 M	99,5	398,16
MP52	11,87	Sodium carbonate 0.1 M	91,2	364,8
MP52	12,10	Sodium carbonate 0.1 M	94,1	376,52

MP52-Ala83	3,72	Sodium acetate 0.1 M	98,4	393,48
MP52-Ala83	4,03	Sodium acetate 0.1 M	94,3	377,2
MP52-Ala83	4,23	Sodium acetate 0.1 M	92,4	369,56
MP52-Ala83	4,43	Sodium acetate 0.1 M	101,9	407,48
MP52-Ala83	4,63	Sodium acetate 0.1 M	0,5	1,88
MP52-Ala83	4,82	Sodium acetate 0.1 M	0,0	0
MP52-Ala83	5,03	Sodium acetate 0.1 M	0,0	0
MP52-Ala83	5,63	Sodium acetate 0.1 M	0,0	0

MP52	3,72	Sodium acetate 0.1 M	104,3	417,2
MP52	3,83	Sodium acetate 0.1 M	94,8	379,2
MP52	4,03	Sodium acetate 0.1 M	94,8	379,2
MP52	4,23	Sodium acetate 0.1 M	97,5	390
MP52	4,43	Sodium acetate 0.1 M	91,2	364,8
MP52	4,63	Sodium acetate 0.1 M	5,6	22,4
MP52	4,82	Sodium acetate 0.1 M	0,1	0,4
MP52	5,03	Sodium acetate 0.1 M	0,0	0
MP52	5,22	Sodium acetate 0.1 M	0,0	0
MP52	5,43	Sodium acetate 0.1 M	0,0	0
MP52	5,63	Sodium acetate 0.1 M	0,0	0

25

Figure 3 shows a comparison of the solubility of MP52 in dependence from the ionic strength of the solvent according to examples 2 and 3 and to the table below. The buffers (sodium acetate-acetic acid and sodium carbonate-sodium bicarbonate) were prepared according to Dawson et al.: Data for biochemical research (Third edition) 1986, p. 429 and p. 439, Clarendon Press, Oxford. In solvents with high ionic strength (0.1 M, see also table corresponding to Fig. 2), protein solubilities of 200 µg/ml or more are achievable at pH values below 4.5 and above 10.3. In solvents with lower ionic strength (0.01 M, see also table below), protein solubilities of about 200 µg/ml or more are achievable at pH values below 5.2 and above 9.5.

35

SAMPLE	pH	SOLVENT	RECOVERY (%)	RECOVERY (µg/ml)
MP52	7,50	0.01M Sodium carbonate	0,0	0,08
MP52	8,00	0.01M Sodium carbonate	3,5	14
MP52	8,50	0.01M Sodium carbonate	1,6	6,32

MP52	9,00	0.01M Sodium carbonate	20,7	82,76
MP52	9,50	0.01M Sodium carbonate	48,7	194,6
MP52	11,00	0.01M Sodium carbonate	80,5	322,16
MP52	3,72	0.01M Sodium acetate	98,4	393,48
MP52	4,05	0.01M Sodium acetate	100,9	403,56
MP52	4,20	0.01M Sodium acetate	95,1	380,28
MP52	4,55	0.01M Sodium acetate	94,8	379,2
MP52	4,85	0.01M Sodium acetate	92,0	367,92
MP52	5,15	0.01M Sodium acetate	75,5	302,16
MP52	5,45	0.01M Sodium acetate	6,9	27,56
MP52	5,65	0.01M Sodium acetate	0,1	0,52

Figure 4 shows, according to examples 3 and 5, the stability of MP52 and MP52-Ala83 in different buffers (10 mM HCl, 10 mM sodium acetate pH 4.0 and 10 mM sodium citrate pH 4.0) after two weeks of storage at 20°C as determined by RP-HPLC analysis.

40 The high main peaks representing MP52 (or MP52-Ala83, respectively) are present at about 17-23 min (MP52) and at about 11-18 min (MP52-Ala83). Additional Peaks (Forepeaks) appearing in front of the main peak and in deviation to the untreated Reference Standards indicate degradation products of the proteins. Significant protein degradation appears in 10 mM sodium citrate, whereas the protein stability is improved

45 in 10 mM HCl and especially in 10 mM sodium acetate buffer.

Figure 5 shows, according to examples 3 and 6, the stability of MP52 and MP52-Ala83 in dependency from the ionic strength of the used buffer/solvent as determined by RP-HPLC analysis. The degradation of MP52 in 10 mM and 20 mM sodium acetate pH 4.0

50 after two weeks of storage at 20°C as well as the degradation of MP52-Ala83 in 10 mM and 20 Sodium citrate pH 4.0 after one week of storage at 20°C are shown as nonlimiting examples. The high main peak representing MP52 (or MP52-Ala83, respectively) is present at about 15-20 min. Additional Peaks (Forepeaks) appearing in front of the main peak and in deviation to the untreated Reference Standards indicate

55 degradation products of the proteins. The protein stability is good in 10 mM sodium acetate but is even better if the proteins are stored in a buffer with moderate ionic strength (20 mM sodium acetate). Even in buffers which are generally not suited for storage of the morphogenetic proteins (sodium citrate), an enhancement of the protein stability is achievable in the buffer with moderate (20 mM) ionic strength.

Figure 6 shows, according to examples 3 and 7, the stability of MP52 and MP52-Ala83 at pH11, pH12 and pH13 after 0 and 90 min as determined by RP-HPLC analysis. The high main peak representing MP52 (or MP52-Ala83, respectively) is present at about 15-20 min. Additional Peaks (Forepeaks) appearing in front of the main peak and in deviation to the untreated Reference Standards indicate degradation products of the proteins. The proteins are stable at high pH values at least up to pH12, for shorter periods not exceeding 90 min also at pH13.

Figure 7 shows radiographs of rat cranial defects filled with osteoinductive materials 8 weeks post operation according to example 9. A: untreated defects, B: defects treated with collagen sponges alone; C: defects filled with collagen + dimeric MP52; D: defects filled with collagen + monomeric MP52 (MP52-Ala83). Whereas no bone regeneration is visible in untreated (7 A) or solely matrix treated (7B) defects, osteoregeneration is noticeable in cranial defects filled with collagen and morphogenetic protein (7C and 7D).

Example 1: Isoelectric focusing

Isoelectric Focusing was performed under non reducing conditions by using a "CleanGel IEF" gel (Pharmacia, Cat. No. 18-1035-32). Prior to use, the dried gel was rehydrated for 8 hours in a 40 ml aqueous solution containing 19,2 g Urea, 400 µl NP-40 (10% solution), 100 µl Ampholine pH 3.5-10.0 (Pharmacia, Cat. No. 80-1125-87) and 2,5 ml Ampholine pH 7.0-9.0 (Pharmacia, Cat. No. 80-1125-94). The running conditions were as follows:

Phase	Voltage (V)	Current (mA)	Power (W)	Time (min)
Prefocusing	700	12	8	20
Sample entrance	500	8	8	60
Isoelectric focusing	2000	14	14	150
Band sharpening	2500	14	18	10

500 ng protein were applied per lane. After running, the gel was placed 2 times for 15 min each in fixing solution (115 g/l Trichloroacetic Acid and 35 g/l 5-Sulfosalicylic Acid Dihydrate), washed in distilled water and silver stained (see Fig. 1). For

determination of pI, after IEF one gel was separately cut from the anode side into 1 cm pieces, which were soaked in water for injection for extraction. When the pH's of the extracts were plotted versus the distance from the anode side, a linearity in the pH gradient was observed over the range of 2.5 – 7.5 cm from the anode side. The pI values were determined by measuring the distance between anode (pH 7) and the main band and using linear coherency of pI and distance between anode and main bands. The distance to the anode for the MP52 dimer band was $x = 5.5$ cm and for the MP52-Ala83 band the distance was $x = 3.2$ cm. The used linear equation is $y = 0.217 * x + 6.416$. Therefore, the experimentally determined pI of the MP52 dimer is approximately 7.65 and the pI of MP52-Ala83 is approximately 7.1.

Example 2: Determination of the protein solubility

MP52 and/or MP52-Ala83, previously dissolved in 10 mmol/l HCl, were lyophilized. Lyophilisates were dissolved for equal time periods of 5 min in different solvents (see Fig. 2 and 3) in order to create final protein concentrations of 0.4 mg/ml. Samples were subsequently analysed by RP-HPLC and the recovery rate/amount of dissolved protein was calculated.

Example 3: Reversed Phase HPLC analysis of protein samples

For determination of protein degradation, commonly known Reversed Phase HPLC analysis (RP-HPLC) of samples was performed. RP-HPLC devices of different manufacturers were used. A suitable example for adequate running conditions is: Column: Vydac C18; 5 μ m; 300 Angstrom; 2.1 x 250 mm; Phase 218TP52; Phase A: 0.15% TFA in water; Phase B 0.15% Acetonitril/TFA; Rate: 0.3 ml/min.

Example 4: Influence of different solvents on the solubility of the proteins

MP52, previously dissolved in 10 mmol/l HCl, was lyophilized. Lyophilisates were dissolved for equal time periods of 5 min in the different solvents in order to create final protein concentrations of 0.4 mg/ml. The solubility was compared by using two fixed pH values (pH 10 and pH 4.6, respectively) lying at the border of pH-dependent solubility. Samples were subsequently analysed by RP-HPLC and the recovery rate/amount of dissolved protein was calculated.

According to the table below, no solubility was measured at pH 10, if AMP (2-

Amino-2-methyl-1,3-propanediol-HCl; see Dawson et al.: Data for biochemical research (Third edition) 1986, 437, Clarendon Press, Oxford) or sodium glycine were used as solvents. Good solubility was obtained in sodium carbonate buffer or in unbuffered NaOH solution (pH 10). At pH 4.6, sodium acetate proved to be the better solvent in comparison with sodium citrate.

SAMPLE	pH	SOLVENT	RECOVERY (%)	RECOVERY (µg/ml)
MP52	10	Sodium carbonate 0.1 M	34,7	138,3
MP52	10	AMP 0.1 M	0,1	0,4
MP52	10	Sodium glycine 0.1 M	0,0	0,0
MP52	10	NaOH	97	388
MP52	4,6	Sodium acetate 0.1 M	5,6	22,4
MP52	4,6	Sodium citrate 0.1 M	1,1	0,62

Example 5: Influence of different solvents on protein stability

MP52 and MP52-Ala83 were dissolved in three different solvents, one unbuffered solution (10 mM HCl) and two buffered solutions (10 mM sodium acetate pH 4.0, 10 mM sodium citrate pH 4.0). All samples were stored at 20° C. After two weeks, the samples were subjected to Reversed Phase HPLC analysis (Example 3) to determine any degradation of the proteins. The results are shown in Fig. 4. In comparison with a MP52 or MP52-Ala83 reference standard stored at -80°C, the proteins exhibit a significant degradation pattern if solved in 10 mM sodium citrate, whereas much less degradation can be seen in 10 mM HCl. Best results were obtained by storage in 10 mM Sodium acetate buffer.

Example 6: Influence of buffers having different ionic strength on protein stability

MP52 and MP52-Ala83 were dissolved in 10 or 20 mM sodium acetate, pH 4 or in 10 or 20 mM Sodium citrate, pH 4. All samples were stored at 20° C. After one or two weeks, the samples were subjected to Reversed Phase HPLC analysis (Example 3) to determine any degradation of the proteins. The results are shown in Fig. 5. The protein stability is good in 10 mM sodium acetate but is significantly enhanced if the proteins are stored in a buffer with moderate ionic strength (20 mM sodium acetate). Even in buffers which are generally not suited for storage of the morphogenetic proteins (sodium citrate), an enhancement of the protein stability is achievable in the buffer with the higher ionic strength.

Example 7: Stability of MP52 and MP52-Ala83 at pH 11, pH12, pH13

For stability determination of morphogenetic proteins at basic pH values, MP52 and MP52-Ala83 were dissolved in Na₂HPO₄ buffer. The pH was adjusted with NaOH to either pH11, pH12 or pH13. After 0 and 90 min the samples were subjected to
 5 Reversed Phase HPLC analysis to determine any degradation of the proteins. As it is shown in Fig. 6, in comparison with a MP52 or MP52-Ala83 reference standard, no major alteration of the peak profile could be seen after 0 and 90 min at pH 11 and pH12, whereas a significant increase of forepeaks representing degradation products is clearly visible after 90 min at pH13. However, a major portion of the MP52 main peak
 10 is still present at pH13. Therefore this example proved stability of morphogenetic proteins at high pH values at least up to pH12. Furthermore, these proteins are also stable at pH13 for short periods not exceeding 90 min.

Example 8: Acidic coating of matrix materials for generating an even protein
 15 distribution

This general coating procedure is preferably advantageous for the coating of matrix materials with neutral or basic properties, but can also be used for the coating of acidic carriers.

MP52-Ala83 was dissolved in 10 mM HCl, 10 mM sodium acetate (pH 4) or 20 mM
 20 sodium acetate or combinations thereof to give a final concentration of 1 µg/ml. Optionally the solutions contained one or more of the following additives: 8-15% saccharides, 50-60% alcohols, 10-75% syndets. The solutions were subsequently pipetted to a β-TCP matrix material. 100 ng MP52-Ala83 was used for coating of 100 mg matrix material. The coated β-TCP was air dried for 1 hour at 20° C and finally air-
 25 dried or vacuum-dried to remove any remaining fluid.

Example 9: Acidic coating of a collagen carrier and demonstration of osteoinduction *in vivo*

Absorbable hemostatic collagen sponges (type „Helistat“, Integra Life Sciences, Plainsboro, USA) were cut in small (0.6 cm x 0.6 cm) pieces. Subsequently, the
 30 rough sides of the sponges were coated with 60 µl of either dilution buffer alone (10 mM HCl/20 mM sodium acetate, pH 4.0) as a negative control, monomeric MP52-Ala83 (500µg/ml in dilution buffer) or dimeric MP52 (500µg/ml in dilution

buffer). The sponge matrices were air dried under sterile conditions. The ability of these osteoinductive materials to induce new bone growth *in vivo* was subsequently evaluated by using a rat cranial defect study. In this well established animal model, circular bone defects are drilled into the cranium of rats and matrix implants coated with morphogenetic proteins are placed within the naturally nonhealing holes. After a couple of weeks, the effectivity of the osteoinductive materials to induce new bone growth can be calculated by determination of defect size reduction.

The sponge collagen matrices were rehydrated prior to implantation in 30 μ l phosphate buffered saline (PBS) for 10 min. The implants were finally placed into bilateral defects (diameter 6 mm, each), which have been created in the parietal bones of rats according to a previously described by Mulliken, J.B. and Glowacki, *J. Plast. Reconstr. Surg.* 65: 553-559 (1980). Implants containing pure collagen without any morphogenetic protein served as negative control, as well as defects without implants. After 8 weeks, animals were sacrificed and contact radiographs were taken. The radiographs of the rat cranial defects revealed significant differences (Figure 7). No bone regeneration could be observed in untreated defects (7 A) or defects treated with collagen sponges alone (7 B). Animals in which the cranial defects had been filled with collagen + dimeric MP52 (7 C) showed strong bone growth starting from the defect borders. Comparable osteoinductive effects were noticeable in specimens treated with collagen + monomeric MP52 (MP52-Ala83) (7 D).

Example 10: Basic coating of matrix materials for generating an even protein distribution

This general basic coating procedure is preferably advantageous for the coating of matrix materials with acidic or neutral properties, but can also be used for the coating of basic carriers. Furthermore, MP52 and MP52-Ala83 were dissolved in 10 or 20 mM sodium carbonate/sodium bicarbonate buffer or NaOH (pH 12) to give a final concentration of 1 μ g/ml. Optionally the solutions contained one or more of the following additives: 8-15% saccharides, 50-60% alcohols, 10-75% soaps or syndets. The solutions were subsequently pipetted to a β -TCP matrix material. Within this procedure, 100 ng MP52-Ala83 was used for coating of 100 mg matrix material. The coated β -TCP was air dried for 1 hour at 20° C and finally vacuum-dried to remove any

remaining fluid.

Example 11: Coating of a $\text{Ca}(\text{OH})_2$ carrier at pH 12 and measurement of the biological activity *in vivo*

- 5 Conventional $\text{Ca}(\text{OH})_2$ powder, which is routinely used as a matrix material in tooth repair procedures, was sterilized for 1 hour at 180°C prior to the coating. $\text{Ca}(\text{OH})_2$ exhibits an strongly basic pH of 12 in aqueous solutions. During the coating procedure, 71 mg sterilized $\text{Ca}(\text{OH})_2$ powder was mixed 1:1 with 71 μl solubilized MP52 (3,15 mg/ml) or 71 μl H_2O as a control and incubated to form an osteoinductive material with
- 10 a pH value of 12.

- In order to prove the stability of MP52 at basic pH values, the biological activity of coated MP52 was tested after the coating procedure. The osteoinductive material was neutralized with 1M HCl and subsequently diluted with cell culture medium to release the morphogenetic protein and to produce final protein concentrations of 400 ng/ml and
- 15 133,2 ng/ml MP52. The biological activity of these MP52 solutions was measured *in vitro* by quantification of alkaline phosphatase (ALP) activity using the established mouse cell line MCHT-1/26. The cells were incubated for 3 days in alpha-MEM medium containing 10% FCS, L-Glutamine (20 mM) and penicillin/streptomycin to a confluence of less then 95%. The washed, trypsin treated cells were resuspended in
- 20 the same culture medium and dispensed in 96-well microtiter plates (4.5×10^3 cells per well). The cells were allowed to adhere for 24 hours, washed (alpha-MEM containing L-Glutamin (20 mM) and subjected to the concentrations of MP52 diluted in culture medium. All values of the MP52 samples were compared to a standard of MP52, for which the *in vivo* bone formation activity has been determined. The cells
- 25 were incubated for 72 hours, washed and lysed by incubation in 0.2% Nonidet P-40 detergent and 1 mM MgCl_2 over night. The supernatant was mixed with p-nitrophenylphosphate, the substrate for alkaline phosphatase, and the reaction stopped after 1 hour at 37°C . Changes in absorbance at 405 nm were measured and used as indicator of the relative biological activity. The OD_{405} values of MP52 used
- 30 in the $\text{Ca}(\text{OH})_2$ coating procedure (400ng/ml: 0.629; 133,2 ng/ml: 0.378) are comparable to those of the MP52 standard (400ng/ml: 0.684; 133,2 ng/ml: 0.438), whereas the control showed no absorbance at 450 nm. Therefore this example proved the possibility to coat matrix materials with morphogenetic proteins at high pH values without loss of biological activity.

Example 12: Coomassie staining for detection of the evenness of the coating

The amount of protein bound on the matrix material was visualized by Coomassie staining. Coomassie Brilliant Blue is a synthetic heterocyclic organic stain binding
5 nonspecifically but in an approximately stoichiometric manner to virtually all proteins. Acidified Coomassie Blue dye changes from reddish-brown to blue when it binds to protein. Thus, an uneven protein distribution on the matrix material is represented by a spotted blue pattern.

Coated matrix materials were incubated with Coomassie staining solution (0,5%
10 Coomassie Brilliant Blue R-250 in 40% methanol, 60% PBS) for 20 min at room temperature. Identical uncoated matrix materials were also stained and served as controls. Any excess of dye was removed by washing with 40% methanol/60% PBS until complete destaining of the controls happened.

An absolutely even protein distribution on the matrix materials without any blue
15 spots was recognized by coating in the presence of polysaccharides, especially sucrose. Similar results were obtained in the presence of alcohols, especially ethanol, soaps or syndets.

Claims

1. Osteoinductive material comprising a matrix material and adsorbed on inner
5 or outer surfaces of this matrix material morphogenetic protein(s), wherein the
osteoinductive material is obtainable by contacting the matrix material and the
morphogenetic protein(s) under suitable conditions to keep the protein stable
and dissolved in a solution until dried and thereby allowing that the matrix
material becomes evenly coated with the morphogenetic proteins.
10
2. Osteoinductive material according to claim 1, wherein the morphogenetic protein
contains at least a 7 cysteine region characteristic for TGF- β superfamily proteins.
3. Osteoinductive material according to claim 1 or 2, wherein the morphogenetic
15 protein is a mature protein or a biologically active part or variant thereof.
4. Osteoinductive material according to anyone of claims 1 to 3, wherein the
morphogenetic protein belongs to the TGF- β -, BMP-, GDF-, activin- or GDNF-
family.
20
5. Osteoinductive material according to anyone of claims 1 to 4, wherein the
morphogenetic protein is a dimeric protein.
6. Osteoinductive material according to anyone of claims 1 to 5, wherein the
25 morphogenetic protein is BMP2, BMP7, BMP12, BMP13, MP52 (GDF5) or a
biologically active part or variant thereof.
7. Osteoinductive material according to anyone of claims 1 to 4, wherein the
morphogenetic protein is a protein lacking the cysteine residue which is responsible
30 for dimer formation in the respective naturally occurring proteins.
8. Osteoinductive material according to anyone of claims 1 to 4 and 7, wherein the
morphogenetic protein contains a consensus sequence according to

Formula I: $C(Y)_{25-29}CYYYC(Y)_{25-35}XC(Y)_{27-34}CYC$ or

Formula II: $C(Y)_{28}CYYYC(Y)_{30-32}XC(Y)_{31}CYC$,

wherein C denotes cysteine, Y denotes any amino acid and X denotes any amino acid except cysteine.

5

9. Osteoinductive material according to anyone of claims 1 to 4, 7 and 8, wherein the protein is a monomeric form of MP52.

10

10. Osteoinductive material according to anyone of claim 9, wherein the protein is MP52-Ala83 or a biologically active part or variant thereof.

11. Osteoinductive material according to anyone of the preceeding claims, wherein the matrix material is a biocompatible material.

15

12. Osteoinductive material according to anyone of the preceeding claims, wherein the matrix material is a natural material, a modified natural material or a synthetic material.

20

13. Osteoinductive material according to anyone of the preceeding claims, wherein the matrix material is a porous material.

25

14. Osteoinductive material according to anyone of the preceeding claims, wherein the matrix material comprises at least one of the following substances: a) collagen, b) $Ca(OH)_2$, c) polylactide or polylactide derivatives, d) hyaluronic acid, e) polyoxyethylene polyoxypropylene copolymers f) calcium phosphate, g) a combination of hydroxy apatite and collagen h) a combination of polyglycolic acid and polylactic acid or polylactid derivatives.

30

15. Osteoinductive material according to anyone of the preceding claims, wherein the buffer or solvent used for coating has a ionic concentration of 150 mmol/l or less, 100 mmol/l or less, 80 mmol/l or less, 40 mmol/l or less, 20 mmol/l or less, 10 mmol/l or less, or 5 mmol/l.

16. Osteoinductive material according to anyone of the preceeding claims, wherein the buffer or solvent used for coating further comprises saccharides.
- 5 17. Osteoinductive material according to anyone of the preceeding claims, wherein the buffer or solvent used for coating further comprises alcohols or other organic solvents.
- 10 18. Osteoinductive material according to anyone of the preceeding claims, wherein the buffer or solvent used for coating further comprises soaps or syndets.
19. Osteoinductive material according to any of the preceeding claims, wherein the morphogenetic proteins are covalently or noncovalently linked to polyethylene glycols.
- 15 20. Osteoinductive material according to anyone of the preceeding claims, wherein the buffer or solvent used for coating is capable of maintaining a pH below 5.2.
- 20 21. Osteoinductive material according to claim 20, wherein the buffer or solvent used for coating contains HCl or sodium acetate.
22. Osteoinductive material according to anyone of the preceeding claims, wherein the buffer or solvent used for coating is capable of maintaining a pH above 9.5.
- 25 23. Osteoinductive material according to claim 22, wherein the buffer or solvent used for coating contains NaOH or sodium carbonate/sodium bicarbonate.
- 30 24. Process for the production of an osteoinductive material according to claims 1 to 21, said process comprising contacting a matrix material with a solution of a morphogenetic protein characterized in that substances contained in said solution are selected to enable adjustment of the pH of the solution to below 5.2 even when in contact with the matrix material.
25. Process for the production of an osteoinductive material according to claims 1 to 19, 22 and 23, said process comprising contacting a matrix material with a solution of a

morphogenetic protein characterized in that substances contained in said solution are selected to enable adjustment of the pH of the solution to above 9.5 even when in contact with the matrix material.

- 5 26. Use of an osteoinductive material according to claims 1 to 23 for indications in which monomeric or dimeric morphogenetic proteins have been proven to be useful.

28. März 2003

EPO - Munich
75

28. März 2003

Figure 1






Figure 2




3111

Figure 3




4/11

Figure 4




5111


MP52
Reference Standard



MP52
10 mM HCl
Time: 2 weeks
Temperature 20° C



MP52
10 mM Sodium citrate, pH 4.0
Time: 2 weeks
Temperature 20° C



MP52
10 mM Sodium acetate, pH 4.0
Time: 2 weeks
Temperature 20° C




Figure 5


Chromatogram of BP52-wt453 Standard. The x-axis represents time in minutes (min) from 0 to 12. The y-axis represents intensity from 0 to 100. The following table lists the retention times of the identified peaks:

Retention Time (min)
3.7223
4.1493
4.4493
4.5493
4.6493
6.11827
10.14183
11.20078
12.22814


Chromatogram of the sample showing several peaks. The x-axis is labeled 'min' and ranges from 0 to 70. The y-axis is labeled 'mV' and ranges from -50 to 100. Peaks are labeled with retention times: 4.121, 4.133, 4.144, 5.127, 6.123, 6.131, 8.1274, 8.1322, and 10.1281. A large peak is visible around 55 minutes.

7/11


MP52
Reference Standard



MP52
10 mM Sodium acetate, pH 4.0
Time: 2 weeks
Temperature 20° C




MP52
20 mM Sodium acetate, pH 4.0
Time: 2 weeks
Temperature 20° C




8/11

Figure 6




9/11


MP52-Ala83
pH 13, 0 min




MP52-Ala83
pH 13, 90 min




MP52
Reference Standard



MP52
pH 11, 0 min




MP52
pH 11, 90 min




10111


MP52
pH 12, 0 min




MP52
pH 12, 90 min



MP52
pH 13, 0 min




MP52
pH 13, 90 min



MM

Figure 7



28. März 2003

EPO - Munich
75

28. März 2003

SEQUENCE LISTING

<110> Biopharm Ges.zur biotechnologischen Entwicklung von Pharmaka mbH

<120> Improved osteoinductive materials

<130> 29725P EP

<140>

<141>

<150>

<151> 2003-03-28

<160> 2

<170> PatentIn Ver. 2.1

<210> 1

<211> 2703

<212> DNA

<213> Homo sapiens

<220>

<221> CDS

<222> (640)..(2142)

<400> 1

```
ccatggcctc gaaagggcag cgggtgatttt ttccacataa atatatcgca cttaaagtga 60
tttagacagc atgacatcag agagtaatta aattggtttg ggttggaatt ccgtttccaa 120
ttcctgagtt caggtttgta aaagattttt ctgagcacct gcaggcctgt gagtgtgtgt 180
gtgtgtgtgt gtgtgtgtgt gtgtgtgtga agtattttca ctggaaagga ttcaaaacta 240
gggggaaaaa aaaactggag cacacaggca gcattacgcc attcttcctt cttggaaaaa 300
tcctcagcc ttatacaagc ctccctcaag ccctcagtca gttgtgcagg agaaaggggg 360
cggttggctt tctcctttca agaacgagtt attttcagct gctgactgga gacggtgcac 420
gtctggatac gagagcattt ccactatggg actggataca aacacacacc cggcagactt 480
caagagtctc agactgagga gaaagccttt ccttctgctg ctactgctgc tgccgctgct 540
tttgaaagtc cactcctttc atgggttttc ctgccaaacc agaggcacct ttgctgctgc 600
```


cgctgttctc tttggtgtca ttcagcggct ggccagagg atg aga ctc ccc aaa	654
Met Arg Leu Pro Lys	
1 5	
ctc ctc act ttc ttg ctt tgg tac ctg gct tgg ctg gac ctg gaa ttc	702
Leu Leu Thr Phe Leu Leu Trp Tyr Leu Ala Trp Leu Asp Leu Glu Phe	
10 15 20	
atc tgc act gtg ttg ggt gcc cct gac ttg ggc cag aga ccc cag ggg	750
Ile Cys Thr Val Leu Gly Ala Pro Asp Leu Gly Gln Arg Pro Gln Gly	
25 30 35	
acc agg cca gga ttg gcc aaa gca gag gcc aag gag agg ccc ccc ctg	798
Thr Arg Pro Gly Leu Ala Lys Ala Glu Ala Lys Glu Arg Pro Pro Leu	
40 45 50	
gcc cgg aac gtc ttc agg cca ggg ggt cac agc tat ggt ggg ggg gcc	846
Ala Arg Asn Val Phe Arg Pro Gly Gly His Ser Tyr Gly Gly Gly Ala	
55 60 65	
acc aat gcc aat gcc agg gca aag gga ggc acc ggg cag aca gga ggc	894
Thr Asn Ala Asn Ala Arg Ala Lys Gly Gly Thr Gly Gln Thr Gly Gly	
70 75 80 85	
ctg aca cag ccc aag aag gat gaa ccc aaa aag ctg ccc ccc aga ccg	942
Leu Thr Gln Pro Lys Lys Asp Glu Pro Lys Lys Leu Pro Pro Arg Pro	
90 95 100	
ggc ggc cct gaa ccc aag cca gga cac cct ccc caa aca agg cag gct	990
Gly Gly Pro Glu Pro Lys Pro Gly His Pro Pro Gln Thr Arg Gln Ala	
105 110 115	
aca gcc cgg act gtg acc cca aaa gga cag ctt ccc gga ggc aag gca	1038
Thr Ala Arg Thr Val Thr Pro Lys Gly Gln Leu Pro Gly Gly Lys Ala	
120 125 130	
ccc cca aaa gca gga tct gtc ccc agc tcc ttc ctg ctg aag aag gcc	1086
Pro Pro Lys Ala Gly Ser Val Pro Ser Ser Phe Leu Leu Lys Lys Ala	
135 140 145	
agg gag ccc ggg ccc cca cga gag ccc aag gag ccg ttt cgc cca ccc	1134
Arg Glu Pro Gly Pro Pro Arg Glu Pro Lys Glu Pro Phe Arg Pro Pro	
150 155 160 165	
ccc atc aca ccc cac gag tac atg ctc tcg ctg tac agg acg ctg tcc	1182
Pro Ile Thr Pro His Glu Tyr Met Leu Ser Leu Tyr Arg Thr Leu Ser	
170 175 180	

gat gct gac aga aag gga ggc aac agc agc gtg aag ttg gag gct ggc	1230
Asp Ala Asp Arg Lys Gly Gly Asn Ser Ser Val Lys Leu Glu Ala Gly	
185 190 195	
ctg gcc aac acc atc acc agc ttt att gac aaa ggg caa gat gac cga	1278
Leu Ala Asn Thr Ile Thr Ser Phe Ile Asp Lys Gly Gln Asp Asp Arg	
200 205 210	
ggc ccc gtg gtc agg aag cag agg tac gtg ttt gac att agt gcc ctg	1326
Gly Pro Val Val Arg Lys Gln Arg Tyr Val Phe Asp Ile Ser Ala Leu	
215 220 225	
gag aag gat ggg ctg ctg ggg gcc gag ctg cgg atc ttg cgg aag aag	1374
Glu Lys Asp Gly Leu Leu Gly Ala Glu Leu Arg Ile Leu Arg Lys Lys	
230 235 240 245	
ccc tcg gac acg gcc aag cca gcg gcc ccc gga ggc ggg cgg gct gcc	1422
Pro Ser Asp Thr Ala Lys Pro Ala Ala Pro Gly Gly Gly Arg Ala Ala	
250 255 260	
cag ctg aag ctg tcc agc tgc ccc agc ggc cgg cag ccg gcc tcc ttg	1470
Gln Leu Lys Leu Ser Ser Cys Pro Ser Gly Arg Gln Pro Ala Ser Leu	
265 270 275	
ctg gat gtg cgc tcc gtg cca ggc ctg gac gga tct ggc tgg gag gtg	1518
Leu Asp Val Arg Ser Val Pro Gly Leu Asp Gly Ser Gly Trp Glu Val	
280 285 290	
ttc gac atc tgg aag ctc ttc cga aac ttt aag aac tcg gcc cag ctg	1566
Phe Asp Ile Trp Lys Leu Phe Arg Asn Phe Lys Asn Ser Ala Gln Leu	
295 300 305	
tgc ctg gag ctg gag gcc tgg gaa cgg ggc agg gcc gtg gac ctc cgt	1614
Cys Leu Glu Leu Glu Ala Trp Glu Arg Gly Arg Ala Val Asp Leu Arg	
310 315 320 325	
ggc ctg ggc ttc gac cgc gcc gcc cgg cag gtc cac gag aag gcc ctg	1662
Gly Leu Gly Phe Asp Arg Ala Ala Arg Gln Val His Glu Lys Ala Leu	
330 335 340	
ttc ctg gtg ttt ggc cgc acc aag aaa cgg gac ctg ttc ttt aat gag	1710
Phe Leu Val Phe Gly Arg Thr Lys Lys Arg Asp Leu Phe Phe Asn Glu	
345 350 355	
att aag gcc cgc tct ggc cag gac gat aag acc gtg tat gag tac ctg	1758
Ile Lys Ala Arg Ser Gly Gln Asp Asp Lys Thr Val Tyr Glu Tyr Leu	
360 365 370	

ttc agc cag cgg cga aaa cgg cgg gcc cca ctg gcc act cgc cag ggc 1806
 Phe Ser Gln Arg Arg Lys Arg Arg Ala Pro Leu Ala Thr Arg Gln Gly
 375 380 385

aag cga ccc agc aag aac ctt aag gct cgc tgc agt cgg aag gca ctg 1854
 Lys Arg Pro Ser Lys Asn Leu Lys Ala Arg Cys Ser Arg Lys Ala Leu
 390 395 400 405

cat gtc aac ttc aag gac atg ggc tgg gac gac tgg atc atc gca ccc 1902
 His Val Asn Phe Lys Asp Met Gly Trp Asp Asp Trp Ile Ile Ala Pro
 410 415 420

ctt gag tac gag gct ttc cac tgc gag ggg ctg tgc gag ttc cca ttg 1950
 Leu Glu Tyr Glu Ala Phe His Cys Glu Gly Leu Cys Glu Phe Pro Leu
 425 430 435

cgc tcc cac ctg gag ccc acg aat cat gca gtc atc cag acc ctg atg 1998
 Arg Ser His Leu Glu Pro Thr Asn His Ala Val Ile Gln Thr Leu Met
 440 445 450

aac tcc atg gac ccc gag tcc aca cca ccc acc nnn tgt gtg ccc acg 2046
 Asn Ser Met Asp Pro Glu Ser Thr Pro Pro Thr Xaa Cys Val Pro Thr
 455 460 465

cgg ctg agt ccc atc agc atc ctc ttc att gac tot gcc aac aac gtg 2094
 Arg Leu Ser Pro Ile Ser Ile Leu Phe Ile Asp Ser Ala Asn Asn Val
 470 475 480 485

gtg tat aag cag tat gag gac atg gtc gtg gag tgc tgt ggc tgc agg 2142
 Val Tyr Lys Gln Tyr Glu Asp Met Val Val Glu Ser Cys Gly Cys Arg
 490 495 500

tagcagcact ggccctctgt cttcctgggt ggcacatccc aagagcccct tctgcactc 2202
 ctggaatcac agaggggtca ggaagctgtg gcaggagcat ctacacagct tgggtgaaag 2262
 gggattccaa taagcttgct cgctctctga gtgtgacttg ggctaaaggc ccccttttat 2322
 ccacaagttc ccctggctga ggattgctgc ccgtctgctg atgtgaccag tggcaggcac 2382
 aggtccaggg agacagactc tgaatgggac tgagtcccag gaaacagtgc tttccgatga 2442
 gactcagccc accattttctc ctcacctggg cttctcagc ctctggactc tcctaagcac 2502
 ctctcaggag agccacaggt gccactgcct cctcaaatca catttggtgcc tggtgacttc 2562
 ctgtccctgg gacagttgag aagctgactg ggcaagagtg ggagagaaga ggagagggct 2622

tggatagagt tgaggagtgt gaggctgtta gactgttaga tttaaatgta tattgatgag 2682

ataaaaagca aaactgtgcc t

2703

<210> 2

<211> 501

<212> PRT

<213> Homo sapiens

<400> 2

Met Arg Leu Pro Lys Leu Leu Thr Phe Leu Leu Trp Tyr Leu Ala Trp
1 5 10 15

Leu Asp Leu Glu Phe Ile Cys Thr Val Leu Gly Ala Pro Asp Leu Gly
20 25 30

Gln Arg Pro Gln Gly Thr Arg Pro Gly Leu Ala Lys Ala Glu Ala Lys
35 40 45

Glu Arg Pro Pro Leu Ala Arg Asn Val Phe Arg Pro Gly Gly His Ser
50 55 60

Tyr Gly Gly Gly Ala Thr Asn Ala Asn Ala Arg Ala Lys Gly Gly Thr
65 70 75 80

Gly Gln Thr Gly Gly Leu Thr Gln Pro Lys Lys Asp Glu Pro Lys Lys
85 90 95

Leu Pro Pro Arg Pro Gly Gly Pro Glu Pro Lys Pro Gly His Pro Pro
100 105 110

Gln Thr Arg Gln Ala Thr Ala Arg Thr Val Thr Pro Lys Gly Gln Leu
115 120 125

Pro Gly Gly Lys Ala Pro Pro Lys Ala Gly Ser Val Pro Ser Ser Phe
130 135 140

Leu Leu Lys Lys Ala Arg Glu Pro Gly Pro Pro Arg Glu Pro Lys Glu
145 150 155 160

Pro Phe Arg Pro Pro Pro Ile Thr Pro His Glu Tyr Met Leu Ser Leu
165 170 175

Tyr Arg Thr Leu Ser Asp Ala Asp Arg Lys Gly Gly Asn Ser Ser Val
180 185 190

Lys Leu Glu Ala Gly Leu Ala Asn Thr Ile Thr Ser Phe Ile Asp Lys

195	200	205
Gly Gln Asp Asp Arg Gly Pro Val Val Arg Lys Gln Arg Tyr Val Phe		
210	215	220
Asp Ile Ser Ala Leu Glu Lys Asp Gly Leu Leu Gly Ala Glu Leu Arg		
225	230	235 240
Ile Leu Arg Lys Lys Pro Ser Asp Thr Ala Lys Pro Ala Ala Pro Gly		
245	250	255
Gly Gly Arg Ala Ala Gln Leu Lys Leu Ser Ser Cys Pro Ser Gly Arg		
260	265	270
Gln Pro Ala Ser Leu Leu Asp Val Arg Ser Val Pro Gly Leu Asp Gly		
275	280	285
Ser Gly Trp Glu Val Phe Asp Ile Trp Lys Leu Phe Arg Asn Phe Lys		
290	295	300
Asn Ser Ala Gln Leu Cys Leu Glu Leu Glu Ala Trp Glu Arg Gly Arg		
305	310	315 320
Ala Val Asp Leu Arg Gly Leu Gly Phe Asp Arg Ala Ala Arg Gln Val		
325	330	335
His Glu Lys Ala Leu Phe Leu Val Phe Gly Arg Thr Lys Lys Arg Asp		
340	345	350
Leu Phe Phe Asn Glu Ile Lys Ala Arg Ser Gly Gln Asp Asp Lys Thr		
355	360	365
Val Tyr Glu Tyr Leu Phe Ser Gln Arg Arg Lys Arg Arg Ala Pro Leu		
370	375	380
Ala Thr Arg Gln Gly Lys Arg Pro Ser Lys Asn Leu Lys Ala Arg Cys		
385	390	395 400
Ser Arg Lys Ala Leu His Val Asn Phe Lys Asp Met Gly Trp Asp Asp		
405	410	415
Trp Ile Ile Ala Pro Leu Glu Tyr Glu Ala Phe His Cys Glu Gly Leu		
420	425	430
Cys Glu Phe Pro Leu Arg Ser His Leu Glu Pro Thr Asn His Ala Val		
435	440	445
Ile Gln Thr Leu Met Asn Ser Met Asp Pro Glu Ser Thr Pro Pro Thr		

450

455

460

Xaa Cys Val Pro Thr Arg Leu Ser Pro Ile Ser Ile Leu Phe Ile Asp
465 470 475 480

Ser Ala Asn Asn Val Val Tyr Lys Gln Tyr Glu Asp Met Val Val Glu
485 490 495

Ser Cys Gly Cys Arg
500

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.